

March 2007

Spezifikation Sorte:
silver jet pro

Specification Type:
silver jet pro

Technisches Datenblatt

Technical Data sheet

| Prüfkriterien | Einheit | Nominal werte | standard opaque | matt | premium matt | premium matt | premium matt | flash dry | photo paper gloss |
|--------------------------|-------------------------|----------------|-----------------|---------|--------------|--------------|--------------|-----------|-------------------|
| | | Nominal Values | | | | | | | |
| Characteristics | Unit | | | | | | | | |
| Flächenmasse Grammage | g/m ² gsm | | 80 | 90 | 95 | 120 | 160 | 210 | 200 |
| Dicke Caliper | µm µm | | 107 | 121 | 125 | 160 | 205 | 179 | 195 |
| Weisse Brightness | % ISO % ISO | | 104 | 104 | 104 | 104 | 104 | 97,6 | 95 |
| Glanz Gloss | % 45° ISO % 45° ISO | | --- | --- | --- | --- | --- | 39 | 66,5 |
| Opazität Opacity | % % | | 92 | 92 | 97 | 99 | 99 | 99 | 92,5 |
| Glätte Smoothness | sec sec | | | 40 - 60 | 60 - 80 | 60 - 80 | 60 - 80 | | |
| Glätte Smoothness | ml/min ml/min | | 250 | | | | | | 0,45 ISO 5627 |

The indicated datas are averages of our papers, the variations of the paper characteristics correspond to the regular standard in production and market.
The technical datas show the current standard.
Due to optimization changes may occur.